

TECHNICAL DATA SHEET

FINE PATCH 35

Fast Drying Cement based Underlayment

DESCRIPTION

Rockbond Fine Patch 35 (RB2.24) is a fast drying cement based underlayment designed for smoothing ridges, patching cracks or holes and featheredge transitions. Suitable for repairing internal concrete floors and smoothing over plywood ceramic tiles or cement sheet.



SPECIAL PROPERTIES

- Easy to use - just add water.
- No priming required
- High adhesion
- Fast setting with 15 minute work time.

PREPARATION

- Sub floor must be free of oil, grease, wax, curing compounds, dust, old adhesives and any other contaminants that may inhibit bonding.

MIXING INSTRUCTIONS

Place a small amount of clean water into a clean pail, then add small amount of powder while mixing to achieve the desired paste-like consistency.

Recommended mix ratio is approx 3.5 litres water per 10 kg powder.

Note: Do not over-water as this will result in a weak and powdery finish.

PACKAGING AND SIZE

Rockbond Rapid Screed (RB2.24) is available in 10kg plastic pails.

COVERAGE

Approximately 8spm @ 1mm thickness per 10kg. Applied as a feather edge, expect to gain anything up to 30sqm depending on texture of substrate.

APPLICATION PROCEDURE

Apply the mixed compound to the substrate using a trowel. Apply from feather-edge up to 3mm thickness. Any imperfections or minor trowel ridges can be removed after 1 hour by gentle sanding. Allow to dry before installing floorcoverings - wipe any sanded areas with a damp cloth to remove dust prior to installing floor coverings. Store in dry area off the ground and out of direct sunlight.

HEALTH AND SAFETY

Always wear gloves and a mask when handling and wash hands thoroughly after use. Clean all equipment with water immediately after use.

TECHNICAL INFORMATION

Should you have any queries, or require further information, please contact our **Technical Sales Team: +64 4 568 5401**

ONLINE SUPPORT www.rockbond.co.nz | **FREEPHONE** 0800 76 25 26 | **EMAIL** sales@rockbond.co.nz

Rockbond SCP Ltd provides the above information in good faith and without warranty. The data represents typical values which can be updated at any time, and this information supersedes previous issues. No liabilities can be accepted for any damage or loss arising from the use of Rockbond SCP Ltd literature or its products, because Rockbond SCP Ltd has no continuous control on how the materials are mixed, placed or cured.

ROCKBOND
MAKING CONCRETE STRONGER