

CEMENTITIOUS PRODUCTS
PRODUCT SELECTION CHART

ROCKBOND



Product Code	Product Name	Packaging		Yield**	Comp Strength (Mpa)**		Application Thickness (mm)			Application Area					Application Method					Consistency		Shrinkage Compensated	Fibre Reinforced
		Standard	Other Size Options		1 Day	28 Days	Min	Max*	Max - Bulkcd	Interior	Exterior	Marine Grade	H2S Resistance	Potable Water	Trowel Screed	Spray	Dry Pack	Pump	Pour	Mortar	Flowable		
1.01-25	Repair Mortar	25kg	–	12.5L	15	60	5	60	N/A	•	•	•			•	•	•			•		•	•
1.02HS-25	Sprayed Concrete HS	25kg	1.4T	11.5L	20	60	10	80	N/A	•	•	•			•	•				•		•	•
1.04-25	GP Grout Plus	25kg	1.4T	12-13L	17-20	65-85	5	70	N/A	•	•	•					•	•	•		•	•	
1.06-25	Micro Concrete	25kg	1.4T	12-13L	10-17	50-70	10	350	550	•	•	•			•			•	•		•	•	
1.08-25	Superflow Grout	25kg	–	12.5-13L	20-25	75-90	0.5	20	N/A	•	•	•						•	•		•	•	
1.10-25	Super Strength Grout	25kg	–	11L	45	120	10	80	300	•	•	•						•	•		•	•	
1.12-20	Waterproof Mortar	20kg	–	9.6L	20	27	5	30	N/A	•	•	•		•	•	•				•		•	•
1.12F-20	Waterproof Render (Fine)	20kg	–	9.6L	20	27	FE	20	N/A	•	•	•		•	•	•				•		•	•
1.18-25	Heritage Mortar	25kg	–	11.5L	20	27	5	30	N/A	•	•	•			•	•				•		•	•
2.03-20	Fast Floor Leveller	20kg	–	11.8L	20	35	1	50	N/A	•								•	•SL		•	•	•
2.06-20	Industrial Floor Screed	20kg	–	11.2L	20	55	5	50	N/A	•	•	•			•			•	•		•	•	•
2.20-20	SL30 Self-Smoothing Screed	20kg	–	13L	12	30	FE	25	N/A	•								•	•SL		•	•	•
2.25-10	Mix & Pour	10kg	–	9.5L	15	20	FE	10	N/A	•	•				•				•		•	•	•
2.26-10	Shield HP	10kg	–	8.8L	15	20	FE	2	N/A	•	•	•	•	•		•					•	•	
2.27-10	Multi-Cote Membrane	10kg	–	8.8L	N/A	N/A	FE	2	N/A	•	•	•	•	•		•					•	•	
2.28-20	Rapid Repair	20kg	–	9.8L	36	45	5	30	N/A	•	•	•	•	•	•		•			•		•	•
3.07-25	Fastrock Accel Grout	25kg	10kg	12.5L	35	80	5	60	N/A	•	•	•						•	•		•	•	
3.08-25	Fastrock Accel Concrete	25kg		11.25L	25	60	15	350	550	•	•	•			•			•	•		•	•	
3.09-10	Fastrock Super Accel Mortar	25kg	10kg	12L	20	60	5	60	N/A	•	•	•			•		•			•		•	•
4.01-25	Underwater Mortar	25kg	–	14L	15	50	10	60	N/A		•	•			•					•			
4.03-25	Underwater Grout	25kg	–	12.75L	12	60	10	60	N/A		•	•						•	•		•		
4.04-25	Underwater Concrete	25kg	–	12.5L	10	60	20	350	550		•	•						•	•		•		
5.03-20	Thixotropic Grout	20kg	1.4T	16.8L	12	40	5	80	N/A	•	•	•			•			•		•		•	
5.03HF-20	Pumping Grout HF	20kg	1.4T	13L	20	70	2	70	N/A	•	•							•	•		•	•	
7.04-15	Fairing Coat	15kg	–	13.5L	1	2	FE	3	N/A	•	•				•	•				•		•	

References:

* Application depths can be a lot deeper than some of those listed, depending on type of application. Please talk to our technical team if you have any questions

** Yields & compressive strengths listed are based on typical water content value, with some listing a common range for standard projects.

It is possible to work outside this range, but needs input from Rockbond's Technical Team.

Notes:

All of rockbond's cementitious products listed above are manufactured in New Zealand, with large stocks of common products held in Auckland, Wellington & Christchurch.

Rockbond are manufacturers of custom-made grout for special applications. If you have an application outside of the above perimeters, please talk to us!

All information on this sheet is subject to Rockbond's standard Terms & Conditions.